



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 26, 2018

Mr. Pete Edmondson
PILLOWFLEX INC.
511 Tommy Lee Cook Road
Palmetto, GA 30268

Reference: Laboratory Test Report
Lab Identification No. 29844
Invoice No. 60981

Dear Mr. Edmondson:

One (1) sample, identified as **PF-31 SYNTHETIC DOWN PILLOW**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 3 Resilient Filling Materials Test. The results are as follows:

Test Results

Vertical Char Lengths

11mm 12mm 11mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 38 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

